

**AI TAKAMUL COMPANY FOR ENGINEERING TESTS AND PROFESSIONAL SAFETY LIMITED**

Basra, North Rumaila, Quality Control Yard - Iraq



**CERTIFICATE OF QUALIFICATION VISUAL AND MAGNETIC PARTICLE INSPECTION AND ULTRASONIC THICKNESS GAUGING INSPECTION & PRESSURE TEST**  
THIS REPORT COMPLIES WITH RECOGNIZED INTERNATIONAL STANDARDS & TECHNICAL REQUIREMENTS

CLIENT:	<b>HALLIBURTON</b>	REPORT No.:	QC-24-01-TSS-004-NDT-008
LOCATION:	<b>TSS WORKSHOP &amp; INSPECTION TEST AREA</b>	STANDARD:	ASTM E709 & ASTM E797 & ASME SECTION V ARTICLE 5,10 & 27 & ASME B31.1
WORK ORDER #	326104072	SPECIFICATION:	Halliburton Acceptance Criteria H2S STANDARD NACE MQ-01-76
DATE OF INSP:	13-Jan-2024	INSP. DUE DATE:	<b>12-Jan-2025</b>
TYPE OF INSPECTION:	<b>VISUAL INSPECTION, PRESSURE TEST AND MAGNETIC PARTICLE INSPECTION AND ULTRASONIC THICKNESS GAUGING</b>		

DESCRIPTION:	BLOCK: 3 1/16" 10K	CHOKE MANIFOLD #	12405205
MANUFACTURER:	WOM	SERIAL NO:	10114244-1

**INSPECTION DETAILS**

Max. Working Pressure:	10,000 PSI	Holding Time:	15 Min
Low pressure:	300 PSI	Holding Time:	05 Min
Pump S.N.:	13119220 Cal DUE. AUG.2024	Pressure Gauge NO.:	468066 Cal DUE. AUG.2024

(a) Normal condition  
Underside (b) Corrosion present on back surface. Reflection echo become wide small by diffused reflection caused by corroded scabrous surface.

A:12'O CLOCK / FORWARD  
B:3'O CLOCK / CENTER  
C :6'O CLOCK / AFT

\* ALL READINGS IN INCH  
\*\*MINIMUM THICKNESS PROVIDED BY CUSTMER

ONLINE TRACEABILITY

POINTS	THICKNESS AT POSITION			MINIMUM THICKNESS
	A	B	C	
0°	4.567	4.576	4.564	4.320
90°	4.549	4.559	4.579	
180°	4.571	4.560	4.549	
270°	4.552	4.571	4.562	

**INSPECTION RESULT**

VT & MPI	Accepted	* ACCORDING TO ASTM E709(70.94158).
UT	Accepted	According to Halliburton Procedure (H2S STANDERD NACE MQ-01-76) ASME SECTION V ARTICLE 5 (ASTM E 797)
BODY	Accepted	*** These Are The Actual Readings Need To Follow As Per Halliburton Acceptance Criteria

**Inspection Evaluation**

**(MPI)** The Above Item Has No Significant Discontinuous At The Time Of Inspection And Found Acceptable Accordance To The Halliburton Specification ASTM E709 (70.94158)  
**U.T-**The Above Item Was Found Acceptable As Per Halliburton Procedure H2S STANDARD NACE MQ-01-76 ASME SECTION V ARTICLE 5 (ASTM E 797)  
**Pressure Test-**The Above Item was Pressure Tested up to 300 PSI A low Pressure Hold for 5 min And Maximum Working pressure 10.000 psi Hold 15 min no Leak was Realized while testing & Pressure Was Stable Accordance To Chart Recorder Attached

**INSPECTION EQUIPMENT DETAILS**

**TECHNICAL DETAILS**

AC YOKE S.N:	201504048	CAL DUE DATE	14-Feb-24	White Contrast WCP 2	MANUFACTUR E	BATCH NO	EXPIRE DATE
Digital Lux Meter WHITE LIGHT	2722003	CAL DUE DATE	16-Feb-24	Black Magnetic Ink 7HF	MANUFAC TURE	BATCH NO	EXPIRE DATE
UT THICKNESS GAUGE:	3997	CAL DUE DATE	16-Feb-24	Fluorescent Magnetic Ink 7HF	1.2 to 2.4 ml/100 ml		
UT TEST BLOCK:	NoBo5087	CAL DUE DATE	16-Feb-24				
ASTM Test Block:	1657	CAL DUE DATE	14-Feb-24				
WHITE LIGHT INTENSITY:	3670 lux						

**PERSON DETAILS**

INSPECTOR NAME:	M.Shahzad Ali	SENIOR INSPECTOR:	NAVEED HUSSAIN	CLIENT:	
QUALIFICATION:	ISO 9001, ISO 14001, UT, VT,	INSPECTION SUPERVISOR:	HANI ALI	HB&SIGN	
SIGNATURE & STAMP:				DATE:	

Original - Client Files Copy / Area Office QC/FN/PT/077 Rev.00 DATED 07.NOV. 2021

