

AI TAKAMUL COMPANY FOR ENGINEERING TESTS AND PROFESSIONAL SAFETY LIMITED

Basra, North Rumaila, Quality Control Yard - Iraq

Tel: +9647810009138 / +9647834964657

Email: op@qualitycontrol-iraq.com / hany.akafi@qualitycontrol-iraq.com



INSPECTION CERTIFICATE FOR LIFTING SUB #PE19896

Client Name:	HALLIBURTON (TSS)	Report No.:	HAL-24-08-RS-DST-001
Acceptance criteria:	DS-1 Volume 4 Fifth Edition	Date of Inspection:	02.AUG.2024
Refrance Standard TSS	ST-GL-HAL-TT-510 REV NO 5.1	Next of Inspection:	01.FEB.2025
TEST EQUIPMENT & CONSUMABLE DETAILS			
WHITE CONTRAST WCP-2	Batch #: 220602 Manufacture: Magnaflux Exp Date: JUN.2025	TECHNICAL DETAILS	Wet Visible Continuous
BLACK INK 7HF	Batch#: 220605 Manufacture: Magnaflux Exp Date: JULY.2025	COIL(1200 AMP-TURNS/IN	SR#22650 Cal.16.APR.2024 Cal Due 15.OCT.2024
FLUORESCENT 14HF	Batch #: 220306 Manufacture: Magnaflux Exp Date: March.2025	A.C HAND YOKE	SR#201504052 Cal.15.APR.2024 Cal Due 14.OCT.2024
INTENSITY METER	SR#R.043943 Cal.17.APR.2024 Cal Due 16.OCT.2024	UV BLACK LIGHT	SR#1898977 Cal.15.APR.2024 Cal Due 14.OCT.2024
LEAD GAGE	SR#AH07KF0027 GAEMAKER LG-5003 Cal.17.APR.2024 Cal Due 16.OCT.2024	THREAD PROFILE GAGE	SR#21336 CAL.Date.17.APR.2024 Cal Due 16.OCT.2024 SR#21335 CAL.Date.17.APR.2024 Cal Due 16.OCT.2024
Magnetic Partical Concentration 7 HF	1.2 TO 2.4 ML/100 ML	UV LIGHT INTENSITY:	3080 µw/cm ²
Magnetic particle concentration flourcent 14 HF	0.1 TO 0.4 ML/100 ML	WMPT Light Intensity:	3630 Lux
MAGNITISUM DIRECTION (LONGITUDENAL)			
METHODOLOGY:	- Through Visual inspection - Dimensional - MPI inspection with Ultraviolet light		

Serial No.	Description	Connection		Result Inspection			Dimensional Inspection													
		Pin	Box	Pin	Box	Body	Pin					Box					Body			
							OD(In)	ID(In)	Neck ϕ(In)	Pin λ(In)	Bevel ϕ(In)	OD(In)	CB ϕ(In)	CB δ(In)	BB ϕ(In)	BB δ(In)	Bevel ϕ(In)	Pin T λ(In)	Box T λ(In)	Overall λ(In)
PE19896	LIFTING SUB	5 1½"ACME	5 ½"ACME	Acc.	Acc.	Acc.	7 ½"	2 ¾"	-	-	-	7 ½"	-	-	-	-	-	7 7/8"	11 7/8"	54 7/8"
																				
Conclusion:		■ 01 LIFTING SUB was found "Acceptable". At time of Inspection Ready For Use.																		

OD	Outside Diameter	ID	Inside Diameter	SRG	Stress Relief Groove	CB	Counter Bore	BB	Bore Back	FB	Float Bore
∅	Diameter	∅	Length	∅	Width	∅	Depth	NP.	Not Present	NA.	Not Applicable
EGR	Elevator Groove Recess	SGR	Slip Groove Recess	CR	Crack	B	Bent	PC	Premium Class	RF	Reface
GT	Galled Thread	TP	Thread Pitting	SP	Seal Pitting	TD	Thread Damage	SD	Seal Damage	M	Mashed
1	100 % Coating	2	99-71 % Coating	3	70-40 % Coating	4	Up to 40 %	5	Nil	WT	Wall Thickness
Colors Code:		White	No Defects	Red	Crack or Extreme Damage.	Blue	Damage	Green	Seal Damage	Yellow	ACFM

Inspector Name:	RAO SOHAIL	Review By					
Qualification:	ASNT Level II (MT, PT, VT)	Senior Inspector:	Naveed Hussain	Supervisor:	Hani Ali	Customer Name:	
Signature:						Customer Signature:	
Original - Client Files		Copy - Area Office		QC/FN/DJ-PB/029 Rev.00 dated 07.Nov2021			

