



INSPECTION CERTIFICATE FOR 5” PUP JOINT

Client Name:	HALLIBURTON (HCT)	Report No.:	HAL-24-06-MS-HCT-2273
Acceptance criteria.	DS-1 Volume 4 Fifth Edition	Date of Inspection:	17.AUG.2024
Refrance Standard HCT	MAN-GL-HAL-HCT-900 REV NO.6.6	Next Inspection Date:	16.FEB.2025
		Halliburton Doc. (Visual Procedure D00305796 Revision W)	
Halliburton Doc. (Dimensional Procedure D00301932 Revision M)		Halliburton Doc. (MPI Procedure D00976850 Revision D)	

TEST EQUIPMENT & CONSUMABLE DETAILS

Item	Batch # / Manufacture / Exp Date	Technical Details	Status / Calibration
WHITE CONTRAST WCP-2	Batch #: 220602 Manufacture: Magnaflux Exp Date: JUN,2025	TECHNICAL DETAILS	Wet Visible Continuous
BLACK INK 7HF	Batch#: 220605 Manufacture: Magnaflux Exp Date: JULY.2025	COIL(1200 AMP-TURNS/IN	SR#22650 Cal.16.APR.2024 Cal Due 15.OCT.2024
FLUORESCENT 14HF	Batch #: 220306 Manufacture: Magnaflux Exp Date: March.2025	A.C HAND YOKE	SR#201504052 Cal.15.APR.2024 Cal Due 14.OCT.2024
INTENSITY METER	SR#R.043943 Cal.17.APR.2024 Cal Due 16.OCT.2024	UV BLACK LIGHT	SR#1898977 Cal.15.APR.2024 Cal Due 14.OCT.2024
LEAD GAGE	SR#AH07KF0027 GAEMAKER LG-5003 Cal.17.APR.2024 Cal Due 16.OCT.2024	THREAD PROFILE GAGE	SR#21336 CAL.Date.17.APR.2024 Cal Due 16.OCT.2024 SR#21335 CAL.Date.17.APR.2024 Cal Due 16.OCT.2024
Magnetic Partical Concentration 7 HF	1.2 TO 2.4 ML/100 ML	UV LIGHT INTENSITY:	3260 µw/cm ²
Magnetic particle concentration flourcent 14 HF	0.1 TO 0.4 ML/100 ML	WMPT Light Intensity:	3520 Lux

MAGNITISUM DIRECTION (LONGITUDENAL)

METHODOLOGY:	<ul style="list-style-type: none"> • Through Visual inspection • Dimensional Inspection 	<ul style="list-style-type: none"> • MPI inspection with Ultraviolet light
--------------	---	---

Serial No.	Description	Connection		Result Inspection			Dimensional Inspection													
		Pin	Box	Pin	Box	Body	Pin					Box					Body			
							OD(In)	ID(In)	Neck ω (In)	Pin λ (In)	Bevel ϕ (In)	OD(In)	CB ϕ (In)	CB δ (In)	BB ϕ (In)	BB δ (In)	Bevel ϕ (In)	Pin T λ (In)	Box T λ (In)	Overall λ (In)
HCT-PJ-007	5” PUP JOINT	4 1/2 IF	4 1/2 IF	Acc.	Acc.	Acc.	7”	3 3/4”	12/32”	4 1/2”	6 2/32”	7”	5 10/32”	5/8”	-	-	6 2/32”	8 1/4”	10 1/8	91 1/2”



Conclusion:	<ul style="list-style-type: none"> ■ 01 PUP JOINT was found “Acceptable”. At time of Inspection Ready For Use.
-------------	---

Abbreviations :

OD Outside Diameter	ID Inside Diameter	SRG Stress Relief Groove	CB Counter Bore	BB Bore Back	FB Float Bore	
ϕ Diameter	λ Length	ω Width	δ Depth	NP. Not Present	NA. Not Applicable	
EGR Elevator Groove Recess	SGR Slip Groove Recess	CR Crack	B Bent	PC Premium Class	RF Reface	
GT Galled Thread	TP Thread Pitting	SP Seal Pitting	TD Thread Damage	SD Seal Damage	M Mashed	
1 100 % Coating	2 99-71 % Coating	3 70-40 % Coating	4 Up to 40 %	5 Nil	WT Wall Thickness	
Colors Code:		White No Defects	Red Crack or Extreme Damage.	Blue Damage	Green Seal Damage	Yellow ACFM

Inspector	M. Sghzad Shaned	Review By				
Qualification:		Senior Inspector:	NAVEED HUSSAIN	Supervisor:	Hani Ali	
Signature:		Customer Name:				
		Customer Signature:				

Original - Client Files Copy - Area Office QC/FN/FLS/03 Rev.00 Dated: 07 Nov 2021

