





Ultrasonic Thickness Gauging Report

Client:	DAQING DRILLING COMPANY	Certificate no:	QC-B-06-25-0335-01-04
Location:	Rig DQ1202	Job Order No:	QC-B-06-25-0335
Date of Examination:	03-6-2025	Next Inspection Due:	02-6-2026

Serial Number	Description of the examined equipment	Result
R20-4756	GAS TANK	Accepted



ANGLES	UT WALL THICKNESS POSITION MEASURED IN MM					MINIMUM THICKNESS
	A	B	C	D	E	
0°	6.53	6.44	6.55	6.32	6.51	A , E 4.34 mm B , C , D 5.7 mm
90°	6.42	6.36	6.52	6.37	6.44	
180°	6.49	6.33	6.47	6.41	6.37	
270°	6.39	6.37	6.50	6.38	6.52	



Equipment Details					
Standard	ASTM E797	Specification:	OEM Data Book	Method	WET
Yoke	Permanent	Serial No:	PY-09	Due Date	11. Nov.2025
White Contrast	WCP-2	Batch No:	008A009	Due Date	April.2026
Black Ink	7HF	Batch No:	008A103	Due Date	Jun.2026
Ultrasonic Thickness Meter	UT-1	Serial No:	5202746	Due Date	11. Nov.2025

INSPECTION EVALUATION

During UT all the readings are within the tolerance and accepted according to the abovementioned specification. Visual and MPI were carried out for the above description and found free of surface defects at the time of inspection

Identification of any part found to have a defect and a description of the defect:

Remarks: Minimum of Wall thickness Provided By OEM

LEEA & ASNT Level II Inspector Name:	Signature:	Authenticating This Report:	
Abdullah Mufeed		Mohamed Abdulla	








Ultrasonic Thickness Gauging Report

Client:	DAQING DRILLING COMPANY	Certificate no:	QC-B-06-25-0335-01-05
Location:	Rig DQ1202	Job Order No:	QC-B-06-25-0335
Date of Examination:	03-6-2025	Next Inspection Due:	02-6-2026

Serial Number	Description of the examined equipment	Result
R20-4759	GAS TANK	Accepted



A:12'O CLOCK / FORWARD
B:3'O CLOCK / CENTER
C:6'O CLOCK / AFT



ANGLES	UT WALL THICKNESS POSITION MEASURED IN MM					MINIMUM THICKNESS
	A	B	C	D	E	
0°	6.44	6.37	6.52	6.41	6.49	A , E 4.34 mm B , C , D 5.7 mm
90°	6.46	6.32	6.48	6.39	6.52	
180°	6.51	6.42	6.44	6.33	6.43	
270°	6.40	6.51	6.54	6.30	6.54	

Equipment Details					
Standard	ASTM E797	Specification:	OEM Data Book	Method	WET
Yoke	Permanent	Serial No:	PY-09	Due Date	11. Nov.2025
White Contrast	WCP-2	Batch No:	008A009	Due Date	April.2026
Black Ink	7HF	Batch No:	008A103	Due Date	Jun.2026
Ultrasonic Thickness Meter	UT-1	Serial No:	5202746	Due Date	11. Nov.2025



INSPECTION EVALUATION

During UT all the readings are within the tolerance and accepted according to the abovementioned specification.

Visual and MPI were carried out for the above description and found free of surface defects at the time of inspection

Identification of any part found to have a defect and a description of the defect:

Remarks: Minimum of Wall thickness Provided By OEM

LEEA & ASNT Level II Inspector Name:	Signature:	Authenticating This Report:	
Abdullah Mufeed		Mohamed Abdulla	








Ultrasonic Thickness Gauging Report

Client:	DAQING DRILLING COMPANY	Certificate no:	QC-B-06-25-0335-01-06
Location:	Rig DQ1202	Job Order No:	QC-B-06-25-0335
Date of Examination:	03-6-2025	Next Inspection Due:	02-6-2026

Serial Number	Description of the examined equipment	Result
C19-2400	GAS TANK	Accepted



A:12'O CLOCK / FORWARD
B:3'O CLOCK / CENTER
C:6'O CLOCK / AFT





ANGLES	UT WALL THICKNESS POSITION MEASURED IN MM					MINIMUM THICKNESS
	A	B	C	D	E	
0°	5.17	5.37	5.36	5.41	5.30	4 mm
90°	5.47	5.51	5.39	5.39	5.46	
180°	5.28	5.30	5.28	5.37	5.38	
270°	5.33	5.47	5.33	5.44	5.35	

Equipment Details					
Standard	ASTM E797	Specification:	OEM Data Book	Method	WET
Yoke	Permanent	Serial No:	PY-09	Due Date	11. Nov.2025
White Contrast	WCP-2	Batch No:	008A009	Due Date	April.2026
Black Ink	7HF	Batch No:	008A103	Due Date	Jun.2026
Ultrasonic Thickness Meter	UT-1	Serial No:	5202746	Due Date	11. Nov.2025

INSPECTION EVALUATION

During UT all the readings are within the tolerance and accepted according to the abovementioned specification.
Visual and MPI were carried out for the above description and found free of surface defects at the time of inspection
Identification of any part found to have a defect and a description of the defect:
Remarks: Minimum of Wall thickness Provided By OEM

LEEA & ASNT Level II Inspector Name:	Signature:	Authenticating This Report:	
Abdullah Mufeed		Mohamed Abdulla	







Ultrasonic Thickness Gauging Report

Client:	DAQING DRILLING COMPANY	Certificate no:	QC-B-06-25-0335-01-07
Location:	Rig DQ1202	Job Order No:	QC-B-06-25-0335
Date of Examination:	03-6-2025	Next Inspection Due:	02-6-2026

Serial Number	Description of the examined equipment	Result
C19-2396	GAS TANK	Accepted



ANGLES	UT WALL THICKNESS POSITION MEASURED IN MM					MINIMUM THICKNESS
	A	B	C	D	E	
0°	5.26	5.30	5.29	5.40	5.28	4 mm
90°	5.34	5.41	5.31	5.33	5.38	
180°	5.39	5.36	5.38	5.42	5.29	
270°	5.28	5.32	5.34	5.37	5.35	


Equipment Details					
Standard	ASTM E797	Specification:	OEM Data Book	Method	WET
Yoke	Permanent	Serial No:	PY-09	Due Date	11. Nov.2025
White Contrast	WCP-2	Batch No:	008A009	Due Date	April.2026
Black Ink	7HF	Batch No:	008A103	Due Date	Jun.2026
Ultrasonic Thickness Meter	UT-1	Serial No:	5202746	Due Date	11. Nov.2025

INSPECTION EVALUATION

During UT all the readings are within the tolerance and accepted according to the abovementioned specification. Visual and MPI were carried out for the above description and found free of surface defects at the time of inspection

Identification of any part found to have a defect and a description of the defect:

Remarks: Minimum of Wall thickness Provided By OEM

LEEA & ASNT Level II Inspector Name:	Signature:	Authenticating This Report:	Signature:
Abdullah Mufeed		Mohamed Abdulla	